

X-FLOW SEAFLEX 64 ULTRAFILTRATION MEMBRANE

MEMBRANE ELEMENT DATASHEET

SEAFLEX HP
ARTICLE CODE: 22F1FL895H

GENERAL INFORMATION

Seaflex 64 is used as pre-treatment for seawater reverse osmosis. Mode of operation is feed-and-bleed with a minor crossflow or dead-end mode with regular backwash (permeate only) and chemically enhanced backwash. The Seaflex 64 module is used in applications for standard seawater with low to moderate TSS and/or organic load.

GENERAL SOLVENT RESISTANCE

Since the resistance of the membrane to solvents strongly depends on the actual process conditions, the indications given below should only be considered as guideline.

Acids	++
Bases	++
Organic esters, ketones, ethers	-
Aliphatic alcohols	+
Aliphatic hydrocarbons	+
Halogenated hydrocarbons	--
Aromatic hydrocarbons	--
Polar organic solvents	--
Oils	++

MEMBRANE CHARACTERISTICS

- Hydrophilic membrane composed of a blend of polyvinylpyrrolidone and polyethersulfone
- A nominal pore size of 20 nm
- Structure asymmetric/microporous
- High performance and a very good anti-fouling behaviour
- Typical permeate quality SDI<3, turbidity <0,1 NTU

CLEANING CHEMICAL RESISTANCE

Sodium Hypochlorite
- Typical 200 ppm, at ≤ 40 °C at ≥ pH 10
- Maximum 500 ppm
- 250.000 ppm hours cumulative; ≥ pH 10

Chlorine Dioxide
- Typical 1 ppm, at ≤ 40 °C
- Maximum 2 ppm
- 90.000 ppm hours cumulative; pH 11

Hydrogen Peroxide
- Typical 200 ppm, at ≤ 40 °C
- Maximum 500 ppm
- 350.000 ppm hours cumulative

Note:
The above figures for oxidant contact represent the membrane resistance to each individual oxidizing agent. The total combined exposure for Sodium Hypochlorite and Chlorine Dioxide will be calculated as follows:

Combined exposure $[NaOCl + ClO_2] = 2.6 \times$
Exposure to ClO_2 (in ppm hours) + Exposure to $NaOCl$ (in ppm hours) < 250.000 ppm hours

As a good working practice and in order to maximise the lifetime of the membrane it is advised to reduce the membrane exposure to oxidising agents to a minimum. Exposure limits are also affected by temperature, pH and the presence of metals. In order not to exceed maximum exposure limits, membranes must be preserved free of any oxidising agent when the plant is stopped.

Acids

Hydrochloric Acid	++
Nitric Acid	++
Sulphuric Acid	++
Phosphoric Acid	++
Acetic Acid	++
Citric Acid	++

pH > 2 during filtration
pH > 1 during cleaning


Bases

Sodium Hydroxide (<4%)	++
Potassium Hydroxide (<4%)	++

pH < 12 during filtration
pH < 13 during cleaning

ELEMENT SPECIFICATIONS

Membrane diameter [mm/mil]	Effective membrane area [m ² /ft ²]	Feed connection D ₀ [mm/Inch]	Module length L ₀ [mm/Inch]	Permeate connection d ₀ [mm/Inch]
0.83 [32.7]	64 [687]	220.0 [8.66]	1537.5 [60.51]	42.6 [1.68]



X-FLOW SEAFLEX 64 ULTRAFILTRATION MEMBRANE

MEMBRANE ELEMENT DATASHEET

OPERATING SPECIFICATIONS

Max. system pressure	Max. trans-membrane pressure	Max. backflush pressure	Temp. range
[kPa/psi]	[kPa/psi]	[kPa/psi]	[°C/°F]
300 [43]	300 [43]	300 [43]	0-40 [32-104]

- Backwash water should be free of particulates and should be of UF permeate quality or better
- Backwash pumps should preferably be made of non-corroding materials, e.g., plastic or stainless steel. If compressed air is used to pressurize the backwash water, do not allow a two-phase air/water mixture to enter the element
- To avoid mechanical damage, do not subject the membrane module or

element to sudden temperature changes, particularly decreasing. Bring the module or element back to ambient operating temperature slowly (max. value 3 °C/min). Failure to adhere to this guideline can result in irreparable damage

Operation of membrane modules at any combination of maximum limits of pH, concentration, pressure or temperature, during cleaning or production, will influence the membrane lifetime.

TECHNICAL SPECIFICATIONS

Weight Specifications

Dry weight of membrane element
ca. 34 kg [75 lbs]

Membrane element filled with water
ca. 66 kg [145 lbs]

Materials of Construction

Housing	PVC white
Flow distributor	PVC/PP
Potting	PU resin
Membrane	PES/PVP

Process Characteristics (Water, 20 °C)

Hydraulic membrane diameter	Crossflow flow rate (*)	Pressure-drop across module at 1 m/s	Pressure-drop across module at 2 m/s
[mm/in]	[m ³ /h/gpm]	[kPa/psi]	[kPa/psi]
0.83 [32.7]	26.9*v [36*v]	64 [9]	136 [20]

(*) superficial velocity (v) in m/s [ft/s]

STORAGE

New membrane modules can be stored as supplied in the original packaging. The membrane modules contain an aqueous preservation solution of glycerine (20wt%) and sodium metabisulfite (1wt%) to prevent dehydration and control bacterial growth. The membrane modules are packed in plastic bags which are vacuum sealed to keep the moisture in the module. Membrane modules should be stored in a dry, normally ventilated place, away from sources of heat ignition and direct sunlight.

Storage temperature should be between 0 and 40 °C. Pentair instructions for transport and storage are to be followed at all times and available upon request. It is recommended to have the membrane modules installed into the UF skids and commissioned as soon as possible. The membrane shelf life is maximum 6 months from the date the modules are announced ready for delivery ex works Pentair warehouse. After expiry of the shelf life all warranties are null and void.



X-FLOW BV

P.O. BOX 739, 7500 AS ENSCHEDE, NETHERLANDS WWW.X-FLOW.COM

Note: The information and data contained in this document are based on our general experience and are believed to be correct. They are given in good faith and are intended to provide a guideline for the selection and use of our products. Since the conditions under which our products may be used are beyond our control, this information does not imply any guarantee of final product performance and we cannot accept any liability with respect to the use of our products. The quality of our products is guaranteed under our conditions of sale. Existing industrial property rights must be observed.
DS SEAFLEX 64 EN 4016 © 2016 Pentair. All Rights Reserved.

